

Wangsan-ro 51, Yongdu-dong, Dongdaemun-gu,

Seoul, Korea

www.katri.re.kr

T: +82-2-3668-3000 F: +82-2-3668-2904

KATRI DOCUMENT SERVICE

TEST REPORT

APPLICANT: HAERAE CO., LTD.

KATRI NO

: SFBB20-00000061

BUYER :

ISSUED DATE

RECEIVED DATE : JAN. 13, 2020

PAGE(S)

: JAN. 31, 2020 : 1 OF 6

APPLICANT'S PROVIDED SAMPLE DESCRIPTION :

ITEM: 60 COTTON LAWN

SUBMITTED FIBER CONTENT: 100 % COTTON

SUBMITTED CARE INSTRUCTION: MACHINE WASH WARM, NORMAL CYCLE,

ONLY NON-CHLORINE BLEACH IF NEEDED, TUMBLE DRY LOW, WARM IRON IF NEEDED

TEST RESULT
#1

FIBER CONTENT (%): AATCC 20A-2018

COTTON 100

<NOTE> MOISTURE REGAIN: 8.00 % COTTON (BASED ON ASTM D 1909 - 2013)

- Continues -

Lim, Hun Jin Director General

Tested by Name : Ryu Si Hyun

X

Technical Manager: Kim Jung Min

~~~





Wangsan-ro 51, Yongdu-dong, Dongdaemun-gu, Seoul, Korea

T : +82-2-3668-3000 F : +82-2-3668-2904

www.katri.re.kr

KATRI DOCUMENT SERVICE

KATRI NO: SFBB20-00000061

PAGE(S): 2 OF 6

TEST RESULT TEST ITEM #1 DIMENSIONAL CHANGE TO WASHING (%): AATCC 135-2018 WARP -2.1WEFT -6.3<NOTE> 1. WASHING CONDITION: MACHINE WASH (41 ± 3) ℃, NORMAL CYCLE, TUMBLE DRY LOW, 3 CYCLES 2. (+) MEANS EXTENSION (-) MEANS SHRINKAGE APPEARANCE AFTER WASHING: AATCC 135-2018 COLOR CHANGE 4.0 SELF STAINING 4.5 **PILLING** 4.5 OVERALL RATING SLIGHT COLOR CHANGE WAS FOUND. <NOTE> WASHING CONDITION: MACHINE WASH (41 ± 3) ℃, NORMAL CYCLE, TUMBLE DRY LOW, 3 CYCLES SKEWNESS CHANGE AFTER WASHING (%): AATCC 179-2019 AFTER 3 CYCLES +2.5 <NOTE> WASHING CONDITION: MACHINE WASH (41 ± 3) °C, NORMAL CYCLE, TUMBLE DRY LOW, 3 CYCLES HAND IRON (GRADE) : IN HOUSE METHOD WARM IRON NO CHANGE (SAFE) FABRIC WEIGHT  $(g/m^2)$ : ASTM D 3776/D3776M-09a(2017) OPTION C 74.5  $(2.20 \text{ oz/vd}^2)$ YARN NUMBER (Tex): ASTM D 1059-2017 WARP 9.6 (61.5 's) WEFT 10.1 (58.3 's) THREAD COUNT (Threads/25 mm): ASTM D 3775-2017 WARP 106 WEFT 86 WIDTH (cm): ASTM D 3774-2018 OPTION B

143.4 (56.5 inch)

<sup>-</sup> Continues -

Korea Apparel Testing & Research Institute, letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the Korea Apparel Testing & Research Institute, name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of Korea Apparel Testing & Research Institute, with respect to services rendered, shall be limited to the amount of consideration paid for each service and not include any consequential damages. This report or certificate does not relieve seller/suppliers from their contractual responsibility with regard to the quality/quantity of this delivery, nor does it prejudice client's right to claim towards seller/suppliers for compensation for any apparent and/or hidden defects not defected during our random inspection or testing. This report is not related to KOLAS accreditation.



Wangsan-ro 51, Yongdu-dong, Dongdaemun-gu, Seoul Korea

T: +82-2-3668-3000 F: +82-2-3668-2904

www.katri.re.kr



KATRI NO: SFBB20-00000061

PAGE(S) : 3 OF 6

| TEST ITEM                                              | TEST RESULT  |  |
|--------------------------------------------------------|--------------|--|
|                                                        | #1           |  |
| COLOR FASTNESS TO LAUNDERING (GRADE) : AATCC 61-2013,  | 2A, 49 ℃     |  |
| SELF STAINING                                          | 4.5          |  |
| COLOR CHANGE                                           | 4.5          |  |
| COLOR STAINING - ACETATE                               | 4.5          |  |
| COLOR STAINING - COTTON                                | 4.0          |  |
| COLOR STAINING - NYLON                                 | 4.5          |  |
| COLOR STAINING - POLYESTER                             | 4.5          |  |
| COLOR STAINING - ACRYLIC                               | 4.5          |  |
| COLOR STAINING - WOOL                                  | 4.5          |  |
| COLOR FASTNESS TO RUBBING (GRADE) : AATCC 8-2016 CROCK | METER METHOD |  |
| DRY                                                    | 4.5          |  |
| WET                                                    | 2.5          |  |
| COLOR FASTNESS TO WATER (GRADE) : AATCC 107-2013       |              |  |
| SELF STAINING                                          | 4.5          |  |
| COLOR CHANGE                                           | 4.5          |  |
| COLOR STAINING - ACETATE                               | 4.5          |  |
| COLOR STAINING - COTTON                                | 4.5          |  |
| COLOR STAINING - NYLON                                 | 4.5          |  |
| COLOR STAINING - POLYESTER                             | 4.5          |  |
| COLOR STAINING - ACRYLIC                               | 4.5          |  |
| COLOR STAINING - WOOL                                  | 4.5          |  |
| COLOR FASTNESS TO CHLORINE BLEACH (GRADE) : AATCC SPOT | TEST         |  |
| COLOR CHANGE                                           | 1.0          |  |
| COLOR FASTNESS TO NON-CHLORINE BLEACH (GRADE) : AATCC  | SPOT TEST    |  |
| COLOR CHANGE                                           | 4.5          |  |

<sup>-</sup> Continues -



Wangsan-ro 51, Yongdu-dong, Dongdaemun-gu,

T: +82-2-3668-3000 F: +82-2-3668-2904

www.katri.re.kr



KATRI NO: SFBB20-00000061

PAGE(S): 4 OF 6

| TEST ITEM                                                                                                                                                                    | TEST RESULT                                         |  |
|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------|--|
|                                                                                                                                                                              | #1                                                  |  |
| DIMENSIONAL CHANGE TO WASHING (%): AATCC 135-2018                                                                                                                            |                                                     |  |
| WARP<br>WEFT                                                                                                                                                                 | -1.1<br>-1.9                                        |  |
| <pre><note> 1. WASHING CONDITION : MACHINE WASH (27 ± 2. (+) MEANS EXTENSION (-) MEANS SHRINKAG</note></pre>                                                                 |                                                     |  |
| APPEARANCE AFTER WASHING : AATCC 135-2018                                                                                                                                    |                                                     |  |
| COLOR CHANGE SELF STAINING PILLING OVERALL RATING                                                                                                                            | 4.0<br>4.5<br>4.5<br>SLIGHT COLOR CHANGE WAS FOUND. |  |
| <note> Washing condition : Machine Wash (27 <math>\pm</math> 3</note>                                                                                                        | ) ℃, GENTLE CYCLE, LINE DRY, 3 CYCLES               |  |
| SKEWNESS CHANGE AFTER WASHING (%): AATCC 179-2019                                                                                                                            |                                                     |  |
| AFTER 3 CYCLES                                                                                                                                                               | +2.0                                                |  |
| <note> washing condition : machine wash (27 <math>\pm</math> 3</note>                                                                                                        | ) ℃, GENTLE CYCLE, LINE DRY, 3 CYCLES               |  |
| HAND IRON (GRADE) : IN HOUSE METHOD                                                                                                                                          |                                                     |  |
| WARM IRON                                                                                                                                                                    | NO CHANGE(SAFE)                                     |  |
| COLOR FASTNESS TO LAUNDERING (GRADE) : Ref. AATCC 6                                                                                                                          | 31-2013, 2A, 30 ℃                                   |  |
| SELF STAINING COLOR CHANGE COLOR STAINING - ACETATE COLOR STAINING - COTTON COLOR STAINING - NYLON COLOR STAINING - POLYESTER COLOR STAINING - ACRYLIC COLOR STAINING - WOOL | 4.5<br>4.5<br>4.5<br>4.0<br>4.5<br>4.5<br>4.5       |  |

<sup>-</sup> Continues -



T: +82-2-3668-3000 F: +82-2-3668-2904

www.katri.re.kr



KATRI NO: SFBB20-00000061

PAGE(S) : 5 OF 6

TEST RESULT TEST ITEM #1

CONCLUSION & RECOMMENDATION :

BASED UPON THE RESULTS, WE RECOMMEND TO READ THE CARE INSTRUCTIONS AS FOLLOWS.

MACHINE WASH COLD GENTLE CYCLE ONLY NON-CHLORINE BLEACH IF NEEDED LINE DRY WARM IRON IF NEEDED

- Continues -



Wangsan-ro 51, Yongdu-dong, Dongdaemun-gu, Seoul, Korea

T: +82-2-3668-3000 F: +82-2-3668-2904

www.katri.re.kr

KATRI DOCUMENT SERVICE

KATRI NO: SFBB20-00000061

PAGE(S): 6 OF 6

## IMAGE



#1