

TEST REPORT

APPLICANT : HAERAE CO., LTD.
BUYER :

KATRI NO : SFBB20-00000099
RECEIVED DATE : JAN. 13, 2020
ISSUED DATE : JAN. 31, 2020
PAGE(S) : 1 OF 6

APPLICANT'S PROVIDED SAMPLE DESCRIPTION :

ITEM: 40 COTTON TWILL
SUBMITTED FIBER CONTENT: 100 % COTTON
SUBMITTED CARE INSTRUCTION: MACHINE WASH WARM, NORMAL CYCLE,
ONLY NON-CHLORINE BLEACH IF NEEDED,
TUMBLE DRY LOW, WARM IRON IF NEEDED

TEST ITEM	TEST RESULT
	#1
FIBER CONTENT (%) : AATCC 20A-2018	
COTTON	100
<NOTE> MOISTURE REGAIN : 8.00 % COTTON (BASED ON ASTM D 1909 - 2013)	

- Continues -



Lim, Hun Jin
Director General

Tested by Name : Hwang Kyu Ri



Technical Manager : Kim Jung Min



Location of Test : Wangsan-ro 51, Yongdu-dong, Dongdaemun-gu, Seoul, Korea

Korea Apparel Testing & Research Institute, letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the Korea Apparel Testing & Research Institute, name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of Korea Apparel Testing & Research Institute, with respect to services rendered, shall be limited to the amount of consideration paid for each service and not include any consequential damages. This report or certificate does not relieve seller/suppliers from their contractual responsibility with regard to the quality/quantity of this delivery, nor does it prejudice client's right to claim towards seller/suppliers for compensation for any apparent and/or hidden defects not detected during our random inspection or testing. This report is not related to KOLAS accreditation.

KATRI NO : SFBB20-00000099
 PAGE(S) : 2 OF 6

TEST ITEM	TEST RESULT
#1	
DIMENSIONAL CHANGE TO WASHING (%) : AATCC 135-2018	
WARP	-4.1
WEFT	-3.7
<NOTE> 1. WASHING CONDITION : MACHINE WASH (41 ± 3) °C, NORMAL CYCLE, TUMBLE DRY LOW, 3 CYCLES 2. (+) MEANS EXTENSION (-) MEANS SHRINKAGE	
APPEARANCE AFTER WASHING : AATCC 135-2018	
COLOR CHANGE	4.0
SELF STAINING	4.5
PILLING	4.5
OVERALL RATING	SLIGHT COLOR CHANGE WAS FOUND.
<NOTE> WASHING CONDITION : MACHINE WASH (41 ± 3) °C, NORMAL CYCLE, TUMBLE DRY LOW, 3 CYCLES	
SKEWNESS CHANGE AFTER WASHING (%) : AATCC 179-2019	
AFTER 3 CYCLES	+1.8
<NOTE> WASHING CONDITION : MACHINE WASH (41 ± 3) °C, NORMAL CYCLE, TUMBLE DRY LOW, 3 CYCLES	
HAND IRON (GRADE) : IN HOUSE METHOD	
WARM IRON	NO CHANGE(SAFE)
FABRIC WEIGHT (g/m ²) : ASTM D 3776/D3776M-09a(2017) OPTION C	
	122 (3.61 oz/yd ²)
YARN NUMBER (Tex) : ASTM D 1059-2017	
WARP	13.8 (42.8 's)
WEFT	13.9 (42.5 's)
THREAD COUNT (Threads/25 mm) : ASTM D 3775-2017	
WARP	144
WEFT	72
WIDTH (cm) : ASTM D 3774-2018 OPTION B	
	158.7 (62.5 inch)

- Continues -

Korea Apparel Testing & Research Institute, letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the Korea Apparel Testing & Research Institute, name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of Korea Apparel Testing & Research Institute, with respect to services rendered, shall be limited to the amount of consideration paid for each service and not include any consequential damages. This report or certificate does not relieve seller/suppliers from their contractual responsibility with regard to the quality/quantity of this delivery, nor does it prejudice client's right to claim towards seller/suppliers for compensation for any apparent and/or hidden defects not detected during our random inspection or testing. This report is not related to KOLAS accreditation.

KATRI NO : SFBB20-00000099

PAGE(S) : 3 OF 6

TEST ITEM	TEST RESULT
#1	
COLOR FASTNESS TO LAUNDERING (GRADE) : AATCC 61-2013, 2A, 49 °C	
SELF STAINING	4.5
COLOR CHANGE	4.5
COLOR STAINING - ACETATE	4.5
COLOR STAINING - COTTON	4.5
COLOR STAINING - NYLON	4.5
COLOR STAINING - POLYESTER	4.5
COLOR STAINING - ACRYLIC	4.5
COLOR STAINING - WOOL	4.5
COLOR FASTNESS TO RUBBING (GRADE) : AATCC 8-2016 CROCKMETER METHOD	
DRY	4.5
WET	2.5
COLOR FASTNESS TO WATER (GRADE) : AATCC 107-2013	
SELF STAINING	4.5
COLOR CHANGE	4.5
COLOR STAINING - ACETATE	4.5
COLOR STAINING - COTTON	4.5
COLOR STAINING - NYLON	4.5
COLOR STAINING - POLYESTER	4.5
COLOR STAINING - ACRYLIC	4.5
COLOR STAINING - WOOL	4.5
COLOR FASTNESS TO CHLORINE BLEACH (GRADE) : AATCC SPOT TEST	
COLOR CHANGE	1.0
COLOR FASTNESS TO NON-CHLORINE BLEACH (GRADE) : AATCC SPOT TEST	
COLOR CHANGE	4.5

- Continues -

KATRI NO : SFBB20-00000099

PAGE(S) : 4 OF 6

TEST ITEM	TEST RESULT
	#1
DIMENSIONAL CHANGE TO WASHING (%) : AATCC 135-2018	
WARP	-2.8
WEFT	-2.5
<NOTE> 1. WASHING CONDITION : MACHINE WASH (27 ± 3) °C, GENTLE CYCLE, LINE DRY, 3 CYCLES 2. (+) MEANS EXTENSION (-) MEANS SHRINKAGE	
APPEARANCE AFTER WASHING : AATCC 135-2018	
COLOR CHANGE	4.0
SELF STAINING	4.5
PILLING	4.5
OVERALL RATING	SLIGHT COLOR CHANGE WAS FOUND.
<NOTE> WASHING CONDITION : MACHINE WASH (27 ± 3) °C, GENTLE CYCLE, LINE DRY, 3 CYCLES	
SKEWNESS CHANGE AFTER WASHING (%) : AATCC 179-2019	
AFTER 3 CYCLES	+1.8
<NOTE> WASHING CONDITION : MACHINE WASH (27 ± 3) °C, GENTLE CYCLE, LINE DRY, 3 CYCLES	
HAND IRON (GRADE) : IN HOUSE METHOD	
WARM IRON	NO CHANGE(SAFE)
COLOR FASTNESS TO LAUNDERING (GRADE) : REF. AATCC 61-2013, 2A, 30 °C	
SELF STAINING	4.5
COLOR CHANGE	4.5
COLOR STAINING - ACETATE	4.5
COLOR STAINING - COTTON	4.5
COLOR STAINING - NYLON	4.5
COLOR STAINING - POLYESTER	4.5
COLOR STAINING - ACRYLIC	4.5
COLOR STAINING - WOOL	4.5

- Continues -

KATRI NO : SFBB20-00000099

PAGE(S) : 5 OF 6

TEST ITEM	TEST RESULT
-----------	-------------

#1

CONCLUSION & RECOMMENDATION :

BASED UPON THE RESULTS, WE RECOMMEND TO READ THE CARE INSTRUCTIONS AS FOLLOWS.

MACHINE WASH COLD
GENTLE CYCLE
ONLY NON-CHLORINE BLEACH IF NEEDED
LINE DRY
WARM IRON IF NEEDED

- Continues -

KATRI NO : SFBB20-00000099
PAGE(S) : 6 OF 6

IMAGE



#1