

T: +82-2-3668-3000 F: +82-2-3668-2904

www.katri.re.kr



## TEST REPORT

APPLICANT: HAERAE CO., LTD.

KATRI NO

: SFBB20-00000040-1

**BUYER** 

ISSUED DATE

RECEIVED DATE: JAN. 13, 2020

PAGE(S)

: JAN. 21, 2020 : 1 OF 5

APPLICANT'S PROVIDED SAMPLE DESCRIPTION

ITEM: ACTIVEWEAR INTERLOCK 240

SUBMITTED FIBER CONTENT: 79.3 % POLYESTER 20.7 % SPANDEX SUBMITTED CARE INSTRUCTION: MACHINE WASH WARM, NORMAL CYCLE,

> ONLY NON-CHLORINE BLEACH IF NEEDED, TUMBLE DRY LOW, WARM IRON IF NEEDED

TEST ITEM	TEST RESULT
	#1
FIBER CONTENT (%) : AATCC 20A-2018	
POLYESTER SPANDEX	82.2 17.8
<note> MOISTURE REGAIN : 0.40 % POLYESTER</note>	R 1.30 % SPANDEX (BASED ON ASTM D 1909 - 2013)

- Continues -

Lim, Hun Jin **Director General** 

Tested by Name: Ryu Si Hyun

Technical Manager: Kim Jung Min





Wangsan-ro 51, Yongdu-dong, Dongdaemun-gu, Seoul, Korea

T: +82-2-3668-3000 F: +82-2-3668-2904

www.katri.re.kr

KATRI DOCUMENT SERVICE

KATRI NO : SFBB20-00000040-1

PAGE(S): 2 OF 5

TEST RESULT TEST ITEM #1 DIMENSIONAL CHANGE TO WASHING (%): AATCC 135-2018 WALE -0.4**COURSE** -1.5<NOTE> 1. WASHING CONDITION: MACHINE WASH (41 ± 3) ℃, NORMAL CYCLE, TUMBLE DRY LOW, 3 CYCLES 2. (+) MEANS EXTENSION (-) MEANS SHRINKAGE APPEARANCE AFTER WASHING: AATCC 135-2018 COLOR CHANGE 4.5 4.5 SELF STAINING PILLING 4.5 OVERALL RATING NO NOTICEABLE CHANGE WAS FOUND. <NOTE> WASHING CONDITION: MACHINE WASH (41 ± 3) °C, NORMAL CYCLE, TUMBLE DRY LOW, 3 CYCLES SKEWNESS CHANGE AFTER WASHING (%): AATCC 179-2019 AFTER 3 CYCLES +1.1 <NOTE> WASHING CONDITION: MACHINE WASH (41 ± 3) °C, NORMAL CYCLE, TUMBLE DRY LOW, 3 CYCLES HAND IRON (GRADE): IN HOUSE METHOD WARM IRON NO CHANGE (SAFE) FABRIC WEIGHT  $(g/m^2)$ : ASTM D 3776/D3776M-09a(2017) OPTION C 158  $(4.66 \text{ oz/yd}^2)$ YARN NUMBER (Tex): ASTM D 1059-2017 3.5 (166.4's) <NOTE> EXCLUSIVE OF SPANDEX THREAD COUNT (Threads/25 mm) : ASTM D 3887-1996(2008) WALE 70 **COURSE** 204 <NOTE> COUNTED THE FACE SIDE OF SAMPLE. WIDTH (cm): ASTM D 3774-2018 OPTION B

## - Continues -

Korea Apparel Testing & Research Institute, letters and reports are issued for the exclusive use of the clients to whom they are addressed. No quotations from reports or use of the Korea Apparel Testing & Research Institute, name is permitted except as expressly authorized in writing. Letters and reports apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. The liability of Korea Apparel Testing & Research Institute, with respect to services rendered, shall be limited to the amount of consideration paid for each service and not include any consequential damages. This report or certificate does not relieve seller/suppliers from their contractual responsibility with regard to the quality/quantity of this delivery, nor does it prejudice client's right to claim towards seller/suppliers for compensation for any apparent and/or hidden defects not defected during our random inspection or testing. This report is not related to KOLAS accreditation.

152.7 (60.1 inch)



Wangsan-ro 51, Yongdu-dong, Dongdaemun-gu, Seoul Korea

T: +82-2-3668-3000 F: +82-2-3668-2904

www.katri.re.kr



KATRI NO : SFBB20-00000040-1

PAGE(S) : 3 OF 5

TEST ITEM -	TEST RESULT
	#1
COLOR FASTNESS TO LAUNDERING (GRADE) : AATCC 61-201	3, 2A, 49℃
SELF STAINING	4.0
COLOR CHANGE	4.5
COLOR STAINING - ACETATE	4.5
COLOR STAINING - COTTON	4.5
COLOR STAINING - NYLON	4.0
COLOR STAINING - POLYESTER	4.5
COLOR STAINING - ACRYLIC	4.5
COLOR STAINING - WOOL	4.5
COLOR FASTNESS TO RUBBING (GRADE) : AATCC 8-2016 CR	OCKMETER METHOD
DRY	4.0
WET	4.5
COLOR FASTNESS TO WATER (GRADE) : AATCC 107-2013	
SELF STAINING	4.5
COLOR CHANGE	4.5
COLOR STAINING - ACETATE	4.5
COLOR STAINING - COTTON	4.5
COLOR STAINING - NYLON	4.5
COLOR STAINING - POLYESTER	4.5
COLOR STAINING - ACRYLIC	4.5
COLOR STAINING - WOOL	4.5
COLOR FASTNESS TO CHLORINE BLEACH (GRADE) : AATCC S	POT TEST
COLOR CHANGE	1.5
COLOR FASTNESS TO NON-CHLORINE BLEACH (GRADE) : AAT	CC SPOT TEST
COLOR CHANGE	4.5

<sup>-</sup> Continues -



T: +82-2-3668-3000 F: +82-2-3668-2904

www.katri.re.kr



KATRI NO : SFBB20-00000040-1

PAGE(S): 4 OF 5

TEST RESULT TEST ITEM #1

CONCLUSION & RECOMMENDATION :

BASED UPON THE RESULTS, WE RECOMMEND TO READ THE CARE INSTRUCTIONS AS FOLLOWS.

MACHINE WASH WARM ONLY NON-CHLORINE BLEACH IF NEEDED TUMBLE DRY LOW WARM IRON IF NEEDED

- Continues -



Wangsan-ro 51, Yongdu-dong, Dongdaemun-gu,

Seoul, Korea

T: +82-2-3668-3000 F: +82-2-3668-2904

www.katri.re.kr



KATRI NO : SFBB20-00000040-1

PAGE(S): 5 OF 5

## IMAGE



#1